



**PROTECTAPEEL**  
**PROTECTAPEEL**  
 PAINT • PROTECT • PEEL

## Deckstrip

**Protectapeel Deckstrip** is a weather resistant strippable protective coating, designed to provide protection for a number of surfaces which can be stored externally for periods up to 12 months. Deckstrip will withstand substantial foot traffic and being skin-tight will prevent staining from paint overspray, spillage and scratching. It can be used over contoured non-skid walkways and, being water resistant, will function satisfactorily when subjected to standing water inside boat moulds.

The product is specially formulated to provide good early onset water resistance, and good UV ageing properties.

**TYPE** - Water dispersion (neutral)

**COLOUR** – Blue or other colours by request.

**HEALTH & SAFETY** - The compound is water-borne, non-toxic and non-flammable in the wet state. The dry film can be disposed of as low hazard. Please see separate Health & Safety Data.

**USE** - Strippable coating for protecting metals, GRP, stoved paints, glass reinforced fibre moulds and components. Deckstrip is suitable for most cured paints used in the Marine Industry. **DO NOT USE** on acrylic surfaces. For all other surfaces please contact our Technical Department.

**APPLICATION** - by LAMBSWOOL ROLLER, apply 2 coats (allowing first to tack off ). **Apply generously to achieve a minimum dry film thickness of 100 microns (0.1mm)**. BY SPRAY with airless spray using 17 thou tip size and 2 box coats. **Do not apply in wet or freezing conditions.**

**REPAIR** - If the Protectapeel film rips, the flap may be lifted and resealed by applying a fresh wet coat to the underside and resealing. Alternatively, cut away and re-apply fresh coating – it will bond to itself.

**EXTERNAL WEATHER RESISTANCE** – Deckstrip is suitable for up to 12 months exposure.

**DRYING TIME** - A dry film thickness of 0.1mm will be tack-free in approximately 2 hours at room temperature. Force drying may be used by restricting the surface temperature to 50°C and using maximum air circulation possible.

**SOLIDS** - 45%.

**REMOVAL** - The dry film can be easily removed either by hand stripping or by pressure hose. Do not remove in freezing conditions as the film may be brittle

**COVERAGE** - One litre/kilo will cover about 5m<sup>2</sup> at a film thickness of 0.1mm (0.004"). Thicker coatings of 0.15mm may be advisable where subject to heavy traffic.

**STORAGE** - Shelf life 12 months. Store at temperatures between 5°C-25°C. **DO NOT ALLOW LIQUID TO FREEZE.**

**CLEAN DOWN** - Clean brushes or rollers in water immediately after use.

**GENERAL NOTE:** It is important that this product is thoroughly evaluated under production conditions before being commercially adopted (Such an evaluation should incorporate a reference to ageing). Users should exercise caution whilst walking on any coating that has become wet. The above recommendations are made in good faith for the guidance of users and are without liability. Any queries should be referred to our Technical Sales Department.

Issue 2

**SPRAYLAT**  
 INTERNATIONAL

1 Bardsley Road, Earlstrees Industrial Estate, Corby,  
 Northamptonshire. NN17 4AR  
 Tel: +44(0)1536 408409 Fax: +44(0)1536 400410

