

TECHNICAL DATA SHEET**STRIPPABLE PROTECTIVE COATINGS**

COMPOUND:	SPRAYLAT E105NF
TYPE:	Water dispersion (neutral)
COLOUR:	White. Other colours available by request.
USE:	Strippable (peelable) coating for masking and protecting non-porous surfaces. The dry film is non-flammable.
TENSILE:	168kgs/cm ² (2400 psi)
ELONGATION:	Minimum of 150%
APPLICATION:	By spray, brush or roller coat (brushing viscosity is greater - please specify at time of order). Recommended dry film thickness 100 microns.
FLAMMABILITY:	When exposed to the presence of a naked flame for a period of 30 seconds, our tests show that the Spraylat E105NF dry film will not support combustion once the source of flame has been removed.
SPRAYING PROPERTIES:	The compound is applied using standard air or airless spray guns, eg. Graco, DeVilbiss, JGA or MBC: (i) pressure feed with an FF or FX nozzle and No. 765 air cap; (ii) suction feed with 306D. Use atomisation pressure of 5-6ATM (75-90 psi). A film of 220 microns (0.009") wet without sags may be applied to a vertical surface
DRYING TIME:	Will vary according to humidity and temperature. The evaporation of water will be speeded by air movement and warmth.
ADHESION:	The adhesion is low
PROCESS:	Spraylat E105NF meets the requirements in processing as mask against sprayed emulsion paints, lacquers, oil or grease.
REMOVAL:	The dry film can be easily removed either by hand stripping or by blowing off with a strong air jet
COVERAGE:	One litre will cover approximately 4 square metres at a dry film thickness of 100 microns.
STORAGE:	Shelf life 12 months. Store at temperatures between 5°C - 25°C. DO NOT ALLOW LIQUID TO FREEZE.
CLEAN DOWN:	Clean bushes, rollers or spray equipment in water immediately after use.

GENERAL NOTE: It is important that this product is thoroughly evaluated under production conditions before being commercially adopted (Such an evaluation should incorporate a reference to ageing). The above recommendations are made in good faith for the guidance of users and are without liability. Any queries should be referred to our Technical Sales Department.

Spraylat International Ltd., 1 Bardsley Road, Earlstrees Ind. Est., Corby, Northants NN17 4AR
Tel: 44 (0)1536 Fax: 44 (0)1536 400410